

FICHA TECNICA

TUBERIA ACERO AL CARBON PARA CALDERA



NORMA: ASTM A192

SIN COSTURA

GRADO A

ESPESOR 3MM / CAL 11

Composición química %

C	Si	Mn	P	S	表面质量 (Surface Quality)
0.12	0.21	0.47	0.016	0.012	PASSED
0.13	0.21	0.48	0.017	0.012	PASSED
0.13	0.22	0.49	0.017	0.013	PASSED

DIMENSIONES

